

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
23 January 2003 (23.01.2003)

PCT

(10) International Publication Number
WO 03/006575 A1

- (51) International Patent Classification⁷: **C09K 19/54** (74) Agent: TOL, Arie, J., W.; Internationaal Octrooibureau B.V., Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).
- (21) International Application Number: **PCT/IB02/02511** (81) Designated States (*national*): CN, JP, KR.
- (22) International Filing Date: **24 June 2002 (24.06.2002)** (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- (25) Filing Language: **English**
- (26) Publication Language: **English**
- (30) Priority Data: **01202653.0** **10 July 2001 (10.07.2001)** **EP**
- (71) Applicant: **KONINKLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).**
- (72) Inventor: **HIKMET, Rifat, A., M.; Internationaal Octrooibureau B.V., Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).**
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*



WO 03/006575 A1

(54) Title: **ANISOTROPIC COMPOSITE COMPRISING A MIXTURE OF A POLYMERIC NETWORK AND AN INORGANIC MATERIAL**

(57) Abstract: The invention pertains to an anisotropic composite comprising a mixture of a) an anisotropic oriented polymeric network with one or more binding moieties obtainable from a liquid crystalline monomer or a liquid crystalline mixture of monomers, at least one of the monomers comprising a polymerizable group selected from acrylate, epoxy, oxetane, vinyl ether, and thiolene, and b) an inorganic material, characterized in that the network has an order parameter S greater than 0.01 and that the inorganic material is a substantially water-insoluble inorganic salt, a free metal particle, or a mixture thereof.

Anisotropic composite comprising a mixture of a polymeric network and an inorganic material

The invention pertains to an anisotropic composite comprising a mixture of a) an anisotropic oriented polymeric network with one or more binding moieties obtainable from a liquid crystalline monomer or a liquid crystalline mixture of monomers, at least one of the monomer comprising a polymerizable group selected from acrylate, epoxy, oxetane, vinyl ether, and thiolene, and b) an inorganic material, to a method for manufacturing this material and its intermediate product, and optical devices comprising said material.

The size quantization effects in semiconductor particles are of great interest. In particles of nanometer size, a gradual transition from bulk to molecular structure occurs as the particle size decreases. The particles which show these quantization effects are often called quantum dots. They show size dependant optical and electronic properties. For example, the band gap of these materials can show increase by several electron volts with respect to the bulk material with decreasing particle size. This is reflected in the absorption and the photo-luminescence spectra of the materials that shift hundreds of nanometers with decreasing particle size. The band gap of these materials has been adjusted to produce composites to obtain electroluminescence. In the case of conductive metal particles optical, properties such as absorption become also size dependant. Various methods have been described for obtaining composites of quantum dots in polymer matrices. Liquid crystalline materials comprising an anisotropic oriented polymeric network with one or more binding moieties obtainable from monomers comprising a polymerizable group selected from acrylate, epoxy, vinyl ether, and thiolene are known in the art. For example, in US 5,188,760 such polymeric networks and their synthesis have been disclosed. It is also known that such networks can form ionic complexes with divalent metal cations, such as disclosed in FR 2,738,249 (WO 97/09295). However, it was found that the order parameter of these network complexes is extremely low, making such complexes unsuitable for use in optical devices.

It is an object of the invention to obtain particles in an ordered polymeric matrix, which show size dependent electrical and/or optical effects. It is also an object of the

present invention to obtain a new type of anisotropic composites. The invention pertains to an anisotropic composite of the aforementioned mixture of a polymeric network and an inorganic material wherein a mixture is comprised of a) an anisotropic oriented polymeric network with one or more binding moieties, obtainable from a liquid crystalline monomer or a liquid crystalline mixture of monomers, at least one of the monomers comprising a polymerizable group selected from acrylate, epoxy, oxetane, vinyl ether, and thiolene, and b) an inorganic material, characterized in that the network has an order parameter S greater than 0.01 and that the inorganic material is a substantially water-insoluble inorganic salt, a free metal particle, or a mixture thereof. The mixtures according to this invention differ from the prior art compounds, such as disclosed in FR 2,738,249 in that they do not contain ionic complexes of binding moieties, such as carboxylate groups, with divalent cations. The present mixture comprises polymeric networks that still contain a binding moiety, preferably stabilized with hydrogen bonds, and chemical cross-links thereby securing a high orientation, as can be expressed as a high order parameter S . Preferred networks comprises a COOH, pyridine, or polyether moiety as the binding group. The mole ratio of the liquid crystalline monomers : the inorganic salt and/or free metal particle is preferably 100:1 to 1:5. More preferably, the mol ratio is 10:1 to 1:1.

The anisotropic composite has a nematic, smectic, discotic, or chiral nematic structure. These network are obtained from monomers, including monomers with acrylate, epoxy, oxetane, vinyl ether, and thiolene groups which are polymerizable, usually by a photopolymerization reaction. When cholesteric networks are desired, the mixture of monomers should comprise an amount of a chiral monomer. Preferred chiral monomers are monomers comprising a chiral center in the spacer connecting the binding moiety and the polymerizable group. An example of such a monomer is C6CA (Fig. 1). The chiral center may also be contained in a monomer without a polymerizable group. Preferably, the monomer or the mixture of monomers is in the thermotropic liquid crystalline phase.

Examples of other monomers are C5A and C6M (Fig. 1), which are monoacrylate and diacrylate compounds, respectively, and due to the hydrogen bonding of the carboxylic groups can form a dimer. Such system shows liquid crystallinity. Other examples of suitable monomers comprising polyether moieties are exemplified in Fig. 2. The examples of Fig. 1 and 2 can be prepared according to the methods disclosed in Prog. Polym. Sci., 21, 1165-1209 (1996). Monomers C5A and C6M and mixtures thereof are crystalline at room temperature and become nematic upon melting. With increasing temperature the

ordinary refractive index (n_o) tends to increase while the extraordinary refractive index (n_e) shows a decrease. These changes are associated with the order parameter S that is related to the clearing temperature. Order parameter S can be calculated from the refractive indices as shown in equation (1)

$$S = C \frac{3(n_e^2 - n_o^2)}{2n_o^2 + n_e^2 - 3} \quad (1)$$

wherein C is a constant related to the polarizability of the molecules. Using equation 1, C can be estimated for various mixtures. In this way, the order parameter S can be determined as a function of reduced temperature (which affects the refractive indices). The order parameter S must be greater than 0.01. Preferably, the order parameter S is greater than 0.1, more preferably greater than 0.4.

The anisotropic networks contain physical (hydrogen bonds) as well as chemical cross-links. Anisotropic networks are formed in the oriented state upon polymerization of the acrylate, epoxy, oxetane, vinyl ether, or thiolene groups. For example, it was found that the birefringence ($\Delta n = n_e - n_o$) of pure C5A shows a large decrease upon polymerization. This decrease is associated with the loss of macroscopic order within the sample. This indicates that physical cross-links formed by hydrogen bonds are not strong enough to maintain the order within the system. It was also found that in a mixture containing 10 wt.% of diacrylate (C6M) the high birefringence is sustained upon polymerization. This proves that a small number of chemical cross-links are enough for maintaining the order within the system. Looking at the temperature dependence of the refractive index of the networks it was found that the birefringence of the network, specially those containing a small amount of C6M, shows a rapid decrease around 110°C. This behavior can be best expressed in terms of the order parameter of the network. It can be assumed that the constant C remains unchanged upon polymerization and its use in equation (1) together with the measured refractive indices was used to determine the order parameter of the network. The determination of C is known in the art and is disclosed in Macromolecules, 95(28), 3313-3327 (1995) and Macromolecules, 92(25), 4194-4199 (1992). It was found that polymerized pure C5A (hydrogen bonds only) has a low order parameter. Networks containing C6M (chemical cross-links) on the other hand show a relatively high order parameter at room temperature. It was also found that up to about 100°C the order parameter remains almost constant before showing a rapid decrease at higher temperatures. The decrease observed at higher temperatures is lower for mixtures containing higher concentrations of C6M. This

indicates that within the mixtures the decrease of the order parameter is caused by the hydrogen bonded C5A molecules. Two peaks which are associated with the free and hydrogen bonded carbonyl bands were observed in the IR spectrum. The peak which appears at around 1733 cm^{-1} originates from the carbonyl bands without hydrogen bonding in the central part of C6M and the acrylate end groups. Hydrogen bonded carbonyl groups of C5A showed a shift of about 48 cm^{-1} and appeared in the IR spectrum at 1685 cm^{-1} . With increasing temperature the band at 1685 cm^{-1} decreased in intensity while the intensity of the band at 1733 cm^{-1} showed an increase. The chemical cross-links help maintaining the hydrogen bonds to a higher extent at elevated temperatures, as a result of which samples containing higher fraction of chemical cross-links sustain a higher degree of order at elevated temperatures.

The invention also pertains to a method for manufacturing the above-mentioned anisotropic composite. This method comprises a first step for the synthesis of an intermediate anisotropic oriented network product having one or more binding moieties, comprising polymerizing a liquid crystalline monomer or a liquid crystalline mixture of monomers, at least one of the monomers comprising a polymerizable group selected from acrylate, epoxy, oxetane, vinyl ether, and thiolene, in the presence of a metal salt, to obtain the anisotropic oriented intermediate polymeric network, or polymerizing the liquid crystalline monomer or the liquid crystalline mixture of monomers in the absence of the metal salt to an anisotropic oriented polymeric network with one or more binding moieties, followed by mixing said network with the metal salt, to obtain the intermediate anisotropic oriented network product.

The metal salt can in principle be any metal salt that is sufficiently soluble in the reaction medium. Preferably, the solubility of the metal salt is greater than 0.02 g per 100 ml of water at room temperature.

In a second step the anisotropic composite of the invention is made by converting the metal salt of the thus made intermediate anisotropic oriented network product to a substantially water-insoluble metal salt, a free metal particle, or a mixture thereof by standard methods known in the art.

The preferred method of preparing the anisotropic composite of the invention is the method wherein the intermediate anisotropic oriented network product is obtained by polymerizing the liquid crystalline monomer or the liquid crystalline mixture of polymers in the absence of the metal salt to an anisotropic oriented polymeric network with one or more

binding moieties, followed by mixing said network with the metal salt, after which the metal salt is converted to a substantially water-insoluble metal salt, a free metal particle, or a mixture thereof.

For example, cadmium atoms were built into the network of C6M and C5A as a soluble cadmium salt, for instance cadmium acetate. Subsequently, the networks containing the cadmium atoms were subjected to H₂S gas and CdS quantum dots within the anisotropic network were produced. Fig. 3 schematically shows the steps of production of anisotropic composites. This reaction can be monitored by IR spectroscopy. Upon building cadmium into the system the ester band at 1685 cm⁻¹, which is indicative of hydrogen bonding, disappeared and a new band at 1530 cm⁻¹, which is indicative for the cadmium complex, appeared. Upon reaction of the network containing cadmium atom it can be seen that the band at 1685 cm⁻¹ appeared again while the band at 1530 cm⁻¹ disappeared indicating the formation of CdS and the re-appearance of the hydrogen bonds. The high birefringence of the sample observed after polymerization decreased to a large extent upon building cadmium into the system. This decrease is associated with the conformational change in the hydrogen bonded C5A dimers. While C5A dimer has a rod-like structure, neutralized compound with a cadmium center rather has a bent structure. The bent conformation of the molecule is the cause of the observed behavior.

Upon formation of CdS quantum dots in the network at room temperature, an increase in the birefringence with respect to that of the cadmium compound is observed. When the temperature dependence of the refractive indices of the composite during the heating cycle is considered, it can be seen that up to about 90°C the refractive indices remains constant. Above this temperature up to about 130°C ordinary refractive index increases while a decrease in the extraordinary refractive index is observed. Above 130°C ordinary refractive index increases while extraordinary refractive index shows a decrease. This behavior is associated with the decrease of the order parameter at higher temperatures. When the sample was cooled to room temperature the extraordinary refractive index increased gradually while the ordinary refractive decreased indicating an increase in the order parameter of the system. The other important effect concerns the mean refractive index [$n_a = (2n_o + n_e)/3$] of the material. After building cadmium into the networks, refractive indices change only marginally. However, after the production of CdS there is a very large increase in the refractive indices observed. Heating to 200°C followed by cooling to room temperature results in an extra increase of the refractive index. Two different methods to determine the order parameter were used. The first method uses the refractive indices as described previously. In order to

estimate the contribution of the network to the measured refractive indices of the composite an isotropic contribution from CdS is assumed (0.05 before heating and 0.064 after heating). These values were subtracted to obtain the contribution to the refractive index from the network. In the second method a 2 wt.% of reactive dye (for instance the dye of Fig. 1 which can be prepared according to Mol. Cryst. Liq., 81(78), 271-277(1981) and can be obtained from BASF) were used in the composites and the order parameter of the dye was determined using the equation below.

$$S = \frac{\epsilon_{\parallel} - \epsilon_{\perp}}{\epsilon_{\parallel} + 2\epsilon_{\perp}} \quad (2)$$

wherein ϵ_{\parallel} and ϵ_{\perp} are the absorbance in the direction parallel and perpendicular to the director, respectively. It was found that in all cases the order parameter estimated for the dye is almost the same as the order parameter estimated using the refractive index values. It was found that the order parameter of the network decreased drastically upon building cadmium. Upon production of CdS the order parameter, increased slightly. When the composite material was heated, the mobility increased and the molecules reorganized to assume the orientation with a higher order parameter, which was also present before building cadmium into the system. At higher temperatures, the order parameter decreased again due to the break up of the hydrogen bonds. Upon cooling, the order parameter reached a value at room temperature, which was higher than that obtained before heating. However, this value remained lower than that obtained for the anisotropic network. This means that the presence of CdS crystals distorts the order within the system and the high order parameter is not recovered.

The anisotropic composite of the invention preferably has the nematic, smectic, discotic, or chiral nematic oriented structure.

The substantially water-insoluble inorganic salt, free metal particles, or mixtures thereof are preferably selected from salts or metal particles of Fe, Cr, Co, Ni, Cu, V, Mn, Pd, Ag, Au, Mo, W, Re, Pt, Rh, Pb, Be, Mg, Ca, Sr, Ba, Ra, Zn, Cd, and Hg. The term "substantially water-insoluble" means that less than 0.01 g of the salt dissolves in 100 ml of water at room temperature. Suitable salts are sulfides, which mostly are substantially insoluble in water.

The invention is further illustrated with the following examples.

Examples

The acrylates such as C5A and C6M were synthesized according to the method of US 5,188,760. The photoinitiator was commercially available Irgacure 651 (ex Ciba Geigy). The uniaxial orientation of the molecules was induced in cells provided with uniaxially rubbed polyimide layers. The cell gap was chosen to be between 1-7 μ m. The refractive index measurements were carried out using an Abbe refractometer which could be thermostated up to 140°C. Birefringence of the samples was measured using a polarizing microscope with a tilting compensator. Refractive indices above 140°C were extrapolated using the birefringence and the mean refractive index. Samples were heated using a Mettler hot stage. A Perkin Elmer UV-Vis spectrometer provided with circular polarizers was used for measuring the optical properties of the materials. Emission spectra of the samples were measured using a Perkin Elmer luminescence spectrometer LS50B. For infrared measurements Nicolet FTIR equipment was used. Dynamic mechanical thermo analysis (DMTA) was performed using a Polymer Laboratories DMTA equipment.

The structure of the acrylates are shown in Fig.1. Various mixtures of the samples were placed in the cells and after inducing long range orientation, the polymerization was initiated using UV radiation from a 10W fluorescent lamp (Philips PL10). The polymerized films were neutralized in a solution containing 3 wt. % of cadmium acetate dihydrate, 40 wt.% of ethanol, 7 wt.% of demineralized water, 50 wt.% of dichloromethane. The samples were immersed in the solution for half a day and rinsed in a mixture containing 42 wt.% of ethanol, 8 wt.% of demineralized water, 50 wt. % of dichloromethane to wash away ions, which were not bound to the network. Subsequently, the samples were dried at room temperature and the remnant of the solvent was removed by heating to 150°C. In order to produce CdS quantum dots, cadmium neutralized networks were placed in a tube with dry H₂S for 4h at atmospheric pressure and room temperature.

The liquid crystalline materials of the invention show a strong photoluminescence with a large Stokes shift and high efficiency. For that reason these materials are very suitable for use in optical devices such as LCD's, emissive displays and optical components such as polarizers and wave plates.

CLAIMS:

1. An anisotropic composite comprising a mixture of a) an anisotropic oriented polymeric network with one or more binding moieties obtainable from a liquid crystalline monomer or a liquid crystalline mixture of monomers, at least one of the monomers comprising a polymerizable group selected from acrylate, epoxy, oxetane, vinyl ether, and thiolene, and b) an inorganic material, characterized in that the network has an order parameter S greater than 0.01 and that the inorganic material is a substantially water-insoluble inorganic salt, a free metal particle, or a mixture thereof.
2. The anisotropic composite of claim 1 wherein the order parameter S is greater than 0.1, preferably greater than 0.4.
3. The anisotropic composite of claim 1 or 2 wherein the binding group comprises a COOH, pyridine, or polyether moiety.
4. The anisotropic composite of any one of claims 1-3 wherein the inorganic material is a conductor or a semi-conductor.
5. The anisotropic composite of any one of claims 1-4 having a nematic, smectic, discotic or chiral nematic structure.
6. A method for manufacturing an intermediate anisotropic oriented network product having one or more binding moieties, comprising polymerizing a liquid crystalline monomer or a liquid crystalline mixture of monomers, at least one of the monomers comprising a polymerizable group selected from acrylate, epoxy, oxetane, vinyl ether, and thiolene, in the presence of a metal salt to the anisotropic oriented intermediate polymeric network, or polymerizing the liquid crystalline monomer or the liquid crystalline mixture of polymers in the absence of the metal salt to an anisotropic oriented oriented polymeric network with one or more binding moieties, followed by mixing said network with the metal salt, to obtain the intermediate anisotropic oriented network product .

7. The method of claim 6 wherein the solubility of the metal salt is greater than 0.02 g per 100 ml of water at room temperature.

5 8. A method for manufacturing the anisotropic composite of any one of claims 1-5 wherein the metal salt of the intermediate anisotropic oriented network product obtained by the method of claim 6 or 7 is converted to a substantially water-insoluble metal salt, a free metal particle, or a mixture thereof.


10 9. The method of claim 8 wherein the intermediate anisotropic oriented network product is obtained by polymerizing the liquid crystalline monomer or the liquid crystalline mixture of polymers in the absence of the metal salt to an anisotropic oriented polymeric network with one or more binding moieties, followed by mixing said network with the metal salt.

15


10. An optical device comprising the anisotropic composite of any one of claims 1-5.

1/5


C6M



C5A



C6CA



DYE






FIG. 1




FIG. 2

3/5





Fig. 3-1
Fig. 3-2
Fig. 3-3

Fig. 3

FIG. 3-1



+



4/5





FIG. 3-2



5/5




FIG. 3-3

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 02/02511

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C09K19/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 188 760 A (HIKMET ET AL) 23 February 1993 (1993-02-23) cited in the application claims ---	1, 6, 10
A	FR 2 738 249 A (COMMISSARIAT ENERGIE ATOMIQUE) 7 March 1997 (1997-03-07) cited in the application page 1 -page 4; claims ---	1
A	GB 2 292 745 A (MERCK PATENT GMBH) 6 March 1996 (1996-03-06) claims ---	1, 5, 10
A	EP 0 501 563 A (PHILIPS NV) 2 September 1992 (1992-09-02) claims ---	1, 5, 10
	--- -/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

G document member of the same patent family

Date of the actual completion of the international search

9 September 2002

Date of mailing of the international search report

16/09/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Serbetsoglou, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IB 02/02511

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 676 879 A (HEYNDERICKX ET AL) 14 October 1997 (1997-10-14) claims ---	1
A	WO 96 25470 A (MERCK PATENT GMBH) 22 August 1996 (1996-08-22) claims ---	1,5,10
A	WO 99 48844 A (ROLIC AG; MERCK PATENT GMBH) 30 September 1999 (1999-09-30) claims ---	1,5,6,10
A	US 5 589 959 A (HIKMET) 31 December 1996 (1996-12-31) claims -----	1,5,6,10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/IB 02/02511

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5188760	A	23-02-1993	NL 9000808 A	01-11-1991
			DE 69128738 D1	26-02-1998
			DE 69128738 T2	16-07-1998
			EP 0451905 A1	16-10-1991
			JP 3070777 B2	31-07-2000
			JP 4227684 A	17-08-1992
FR 2738249	A	07-03-1997	FR 2738249 A1	07-03-1997
			WO 9709295 A1	13-03-1997
GB 2292745	A	06-03-1996	NONE	
EP 0501563	A	02-09-1992	NL 9100336 A	16-09-1992
			EP 0501563 A1	02-09-1992
			JP 5061022 A	12-03-1993
			US 5257127 A	26-10-1993
US 5676879	A	14-10-1997	DE 69017347 D1	06-04-1995
			DE 69017347 T2	21-09-1995
			EP 0423880 A1	24-04-1991
			JP 3192311 A	22-08-1991
WO 9625470	A	22-08-1996	DE 69612609 D1	31-05-2001
			DE 69612609 T2	15-11-2001
			WO 9625470 A1	22-08-1996
			EP 0809682 A1	03-12-1997
			JP 11501056 T	26-01-1999
			US 6218578 B1	17-04-2001
			US 6096241 A	01-08-2000
WO 9948844	A	30-09-1999	AU 3416399 A	18-10-1999
			WO 9948844 A1	30-09-1999
			EP 1066227 A1	10-01-2001
US 5589959	A	31-12-1996	DE 69306201 D1	09-01-1997
			DE 69306201 T2	28-05-1997
			EP 0586014 A1	09-03-1994
			JP 6194635 A	15-07-1994